

REMARKS

Claims 1-7 have been canceled, and new claims 8-14 have been added. The canceled claims have been replaced by corresponding new claims in order to improve the grammatical and idiomatic expression. The specification has been amended editorially by way of a Substitute Specification for improved clarity, including correction of grammatical errors and nonidiomatic expression. The Abstract of the Disclosure has been replaced by a new Abstract in accordance with applicable requirements. Entry of the amendments and examination of the amended application are respectfully requested. Please enter the amendments before calculating the filing fee.

Respectfully submitted,

December 30, 2004

Date



Steven M. Rabin (Reg. No. 29,102)

RABIN & BERDO, P.C.

CUSTOMER NO. 23995

(202) 371-8976

(202) 408-0924 fax

SMR:dj

ABSTRACT OF THE DISCLOSURE

An organic EL display is constituted by providing a stress-relieving layer made of a material having a higher elasticity and a lower refractive index than an adhesive layer at edges of color-converting filters that are constituted from color filter layers alone, or color filter layers and color-converting layers, and are formed on a transparent supporting substrate. As a result, stress arising when bonding the color-converting filters and the organic light-emitting device together, or when there are changes in the environment in which the display is placed is absorbed by the stress-relieving layer, and hence the light-emitting device is not damaged, and moreover reflection at walls of the stress-relieving layer is promoted, and hence there is a reduction in the component of the light emitted by the light-emitting device that escapes sideways. An organic EL display having high reliability and high efficiency is thus provided.

DESCRIPTION

ORGANIC EL DISPLAY

CROSS-REFERENCE TO RELATED APPLICATIONS

- 5 This application incorporates by reference the entire disclosure and content of the corresponding PCT application PCT/JP2003/07563, filed on June 13, 2003. Also incorporated by reference are the entire disclosure and contents of the corresponding earlier Japanese patent application JP PA 2002-084434.

10 TECHNICAL FIELD

- The present invention relates to an organic EL (electroluminescent) display that has high detail and is excellent in terms of visibility, and can be used in a wide range of applications such as a display of mobile terminal equipment or industrial
- 15 measuring equipment.

BACKGROUND ARTREVIEW OF RELATED TECHNOLOGY

- 20 In recent years, color organic EL (electroluminescent) displays with a driving method using thin film transistors (TFTs) have been devised. With a method in which the light is extracted from the side of the substrate on which the TFTs are formed, due to the effect of wiring parts blocking the light, the aperture ratio cannot be raised; recently, a so-called top emission method, in which the light is extracted
- 25 from the ~~opposite side to~~ OF the substrate opposite to that on which the TFTs are

formed, has thus been devised.

On the other hand, a color conversion method in which patterned fluorescent bodies are made to absorb light emitted from an organic EL device and hence fluorescence of a plurality of colors is emitted from the fluorescent bodies has been proposed, and is being developed. With this method, by adopting the top emission method using TFT driving, there is the possibility of being able to provide an organic EL display having yet higher detail and higher brightness. The color displays disclosed in Japanese Patent Application Laid-open No. 11-251059 and Japanese Patent Application Laid-open No. 2000-77191 are examples of such a system.

With such a top emission method using TFT driving, there are problems as follows.

Problem of stress

As a structure of a top emission display using the color conversion method, there has been disclosed a structure in which color-converting filters are disposed facing an upper transparent electrode on an organic light-emitting device with a fixed gap provided therebetween by a columnar gap-adjusting layer disposed therebetween (see Japanese Patent Application Laid-open No. 11-297477). Moreover, one can also envisage a method in which this gap is filled with an oily substance.

However, with the constitution in which a fixed gap is provided, the efficiency of extracting light from the organic light-emitting device is worsened due to there being an air layer having a different refractive index between the organic light-emitting layer and the color-converting layers. Moreover, by filling the gap with an oil, this problem is alleviated, but the display manufacturing process becomes more complicated, and moreover the shock resistance, which is an intrinsic advantage

of an organic EL display that is a completely solid device, is marred, and hence this method cannot be said to be the best.

There is a method of resolving these problems in which an organic light-emitting device, and color-converting filters that face an upper transparent electrode on the organic light-emitting device are bonded together via an adhesive layer; however, with this structure, there is a problem of the light-emitting device being damaged by stress arising, for example, through changes in the temperature of the environment in which the manufactured display is placed, or during the step of bonding the organic light-emitting device and the color-converting filters together.

10

<

Problem of efficiency of extracting light>

One approach for increasing the efficiency of a display is to improve the efficiency of extracting light to the outside. With the top emission display structure using the color conversion method, one factor in the efficiency of extracting light to the outside dropping is loss in the adhesive layer. This is due to a component of the light that escapes sideways in the adhesive layer in the case that the direction of extracting the light is made to be upward.

15

DISCLOSURE SUMMARY OF THE INVENTION

20

To resolve the above problems, the present invention provides an organic EL display as follows.

~~That is, an~~An organic EL display characterized by comprising includes an organic light-emitting device, which is constituted by forming on top of one another a substrate, thin film transistors that each have a source and a drain, anodes or cathodes

25

that are made of an electrically conductive thin film material and are each connected to the source or the drain on a corresponding one of the thin film transistors, an organic EL light-emitting layer, an upper transparent electrode that is a cathode or anode ~~that is made of a transparent electrically conductive material~~, and at least one passivation layer on the upper transparent electrode, and which is driven by the thin film transistors; The display also includes a color-converting substrate that ~~comprises~~includes a transparent supporting substrate, and color-converting filters that are constituted from color filter layers alone, or color filter layers and color-converting layers, and are formed on the supporting substrate; ~~an~~ An adhesive layer ~~that is~~ is provided between the organic light-emitting device and the color-converting filters, and bonds the organic light-emitting device and the color-converting filters together with the color-converting filters facing the upper transparent electrode of the organic light-emitting device; ~~and a~~ A stress-relieving layer ~~that is~~ is provided between the organic light-emitting device and the color-converting filters, and is disposed at edges of the color-converting filters.

Moreover, in the organic EL display, the stress-relieving layer includes one containing a resin having a higher elasticity than the adhesive layer, one having a lower refractive index than the adhesive layer, one having a reverse tapered shape relative to the color filter layers alone, or the color filter layers and the color-converting layers, of the color-converting filters, one that is black, one that is a good thermal conductor, and one that is formed from a polymeric material having a good thermal conductor dispersed therein.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a schematic sectional view showing the constitution of an organic

EL display of the invention.

FIG. 2 is a schematic view showing an example of the layout of a stress-relieving layer of the invention.

FIG. 3 is a schematic sectional view showing the constitution of a comparative example in the invention.

FIG. 1 is a schematic sectional view showing the constitutionDETAILED

DESCRIPTION OF THE PREFERRED EMBODIMENTS

Following is a description of embodiments of an organic EL (electroluminescent) display of the present invention.

FIG. 21 is a schematic sectional view of an organic EL display showing an example embodiment of the layout of a stress-relieving layer of the present invention.

FIG. 3 is a schematic sectional view showing the constitution of a comparative example in the present invention.

In the following description, description is given for the case that lower electrodes are anodes, but it is also possible to make the lower electrodes be cathodes, in which case the film structure is the exact opposite from top to bottom.

BEST MODE FOR CARRYING OUT THE INVENTION

Following is a description of embodiments of an organic EL display of the present invention.

FIG. 1 is a schematic sectional view of an organic EL display showing an embodiment of the present invention.

In the following description, description is given for the case that lower

~~electrodes are anodes, but it is also possible to make the lower electrodes be cathodes, in which case the film structure is the exact opposite from top to bottom.~~

1: Thin film transistor (TFT) substrate and anodes

TFTs are arranged in a matrix on an insulating substrate made of glass,
5 plastic or the like, or a substrate obtained by forming an insulating thin film on a
semiconductive or conductive substrate, and source electrodes are connected to the
anodes in correspondence with the pixels.

The TFTs are of a bottom gate type in which a gate electrode is provided
below a gate insulating film, and have a structure in which a polycrystalline silicon
10 film is used as an active layer.

The anodes are formed on a flattening insulating film formed on the TFTs.
With an ordinary organic EL device, ITO, which is transparent and has a high work
function, is used as the anode material, but in the case of top emission, an electrode of
a metal having high reflectivity (Al, Ag, Mo, W or the like) is used below the ITO.

15

2: Organic EL device

For the organic light-emitting device, one having a layer structure such as the
following is adopted.

- (1) Anodes, organic EL light-emitting layer, cathode
- 20 (2) Anodes, hole injection layer, organic EL light-emitting layer, cathode
- (3) Anodes, organic EL light-emitting layer, electron injection layer, cathode
- (4) Anodes, hole injection layer, organic EL light-emitting layer, electron injection
layer, cathode
- (5) Anodes, hole injection layer, hole transport layer, organic EL light-emitting layer,
25 electron injection layer, cathode

With the top emission color conversion method of the present embodiment, in the above layer structures, the cathode must be transparent in the wavelength region of the light emitted by the organic EL light-emitting layer, the light being emitted via this transparent cathode.

5 The transparent cathode is made to have a constitution in which an ultra-thin film (not more than 10 nm) of an electron-injecting metal selected from alkali metals such as potassium, lithium, and sodium, alkaline earth metals such as ~~potassium~~, calcium, magnesium and strontium, and fluorides and so on thereof, or an alloy thereof with other metals or a compound thereof is used as an electron injection layer,
10 and a transparent electrically conductive film of ITO, IZO or the like is formed thereon.

Publicly-known materials are used as the materials of the various layers of the organic ~~EL~~ light-emitting layer. For example, to obtain luminescence from blue to blue/green in color, for example a fluorescent whitening agent of benzothiazole
15 type, benzimidazole type, benzoxazole type or the like, a metal chelated oxonium compound, a styrylbenzene type compound, an aromatic dimethyldene type compound, or the like is preferably used as the organic EL light-emitting layer.

3: Passivation layer

20 For a passivation layer, a material that is electrically insulating, acts as a barrier against moisture and low-molecular-weight components, has high transparency in the visible region (a transmissivity of at least 50% in a range of 400 to 700 nm), and preferably has a film hardness of at least 2H is used.

For example, an inorganic oxide or inorganic nitride such as SiO_x , SiN_x ,
25 SiN_xO_y , AlO_x , TiO_x , TaO_x or ZnO_x , or the like can be used. There are no particular

limitations on the method of forming the passivation layer, with it being possible to form the passivation layer using a commonly used method such as sputtering, CVD, vacuum deposition, or dipping.

The passivation layer may be a single layer, but the effects will be greater
5 with a passivation layer comprising a plurality of layers formed on top of one another.

The thickness of such a multi-layered passivation layer is preferably 0.3 to 5 μm .

4. Stress-relieving layer

10 The stress-relieving layer may be formed on an upper surface of the color-converting filters, or may be formed on the organic light-emitting device side; however, the organic light-emitting device is constituted from materials that are susceptible to heat and ultraviolet radiation, and hence there will be various constraints in the case of forming the stress-relieving layer on the organic
15 light-emitting device. It is thus more preferable to form the stress-relieving layer on the color-converting filters, for which heat and ultraviolet radiation can be used more easily.

The stress-relieving layer is preferably one that can be formed at edges of the color-converting filters without marring the functions of the color-converting filters,
20 and has higher elasticity than the adhesive layer; examples are polymeric materials that do not contain rigid groups in the unit structure thereof such as polyamide resins such as nylon 6 or nylon 6-6, silicone rubbers, any of various synthetic rubbers, and so on. Specifically, a material having a Young's modulus of not more than 0.3×10^{10} Pa is preferable, more preferably not more than 0.1×10^{10} Pa.

25 A photoresist can also be used if the photoresist contains a straight chain

oligomer not containing rigid groups or a monomer having not more than three functional groups as a raw material thereof, and the three-dimensional crosslink density of the cured material is not very high. By using a photoresist, it becomes easy to form the reverse tapered shape.

5 Alternatively, a photoresist other than this can be used as the stress-relieving layer by being used in a state in which the crosslink density has been made to not become very high through weakening the irradiation with light or the amount of heating.

 Regarding the refractive index of the material used in the stress-relieving
10 layer, by using a material having a lower refractive index than that of the adhesive layer, the amount of light emitted from the device that does not contribute to the brightness of the display due to escaping to the stress-relieving layer side can be reduced. The greater the difference in refractive index to the adhesive, the more preferable, since then light incident at a lower angle can be reflected.

15 To improve the contrast, as a method of coloring the stress-relieving layer, for example a substance that absorbs visible light may be added into the material of the stress-relieving layer. The stress-relieving layer may be formed from a single material, or may be formed from a plurality of materials; for example, one can envisage a method of formation in which an elastic relieving layer is formed from a
20 material for which the reverse tapered shape is easily obtained, and then the surface thereof is coated with a material having a low refractive index.

5. Adhesive layer

 The material of the adhesive layer for bonding together the color-converting
25 filters and the organic light-emitting device is preferably a material that transmits

visible light, and enables formation of the adhesive layer without the color-converting layers or the organic light-emitting device being damaged. For example, an ordinary thermoplastic resin, a thermosetting resin that can be cured by heating between normal temperature and 120°C, a resin that is cured by visible light or joint use of

5 heat and light, or the like can be used.

6. Color-converting filters

1) Color-converting layers

In the present invention, as organic fluorescent colorants, examples of

10 fluorescent colorants that absorb light from the blue to blue/green region emitted from the light emitter and emit fluorescence in the red region are rhodamine type colorants such as Rhodamine B, Rhodamine 6G, Rhodamine 3B, Rhodamine 101, Rhodamine 110, sulforhodamines, Basic Violet 11 and Basic Red 2, cyanine type colorants, pyridine type colorants such as

15 1-ethyl-2-[4-(p-dimethylaminophenyl)-1,3-butadienyl]pyridinium perchlorate (Pyridine 1), oxazine type colorants, and so on. Furthermore, various dyes (direct dyes, acid dyes, basic dyes, disperse dyes, etc.) can also be used if fluorescent.

Examples of fluorescent colorants that absorb light from the blue to

20 blue/green region emitted from the light emitter and emit fluorescence in the green region are coumarin type colorants such as

3-(2'-benzothiazolyl)-7-diethylaminocoumarin (Coumarin 6),

3-(2'-benzoimidazolyl)-7-N,N-diethylaminocoumarin (Coumarin 7),

3-(2'-N-methylbenzoimidazolyl)-7-N,N-diethylaminocoumarin (Coumarin 30) and

25 2,3,5,6-tetrahydro-8-trifluoromethylquinolizino-(9,9a,1-g)coumarin

(Coumarin 153), and Basic Yellow 51, which is a coumarin colorant type dye, and also naphthalimide type colorants such as Solvent Yellow 11 and Solvent Yellow 116, and so on. Furthermore, various dyes (direct dyes, acid dyes, basic dyes, disperse dyes, etc.) can also be used if fluorescent.

5 2) Matrix resin

Next, a matrix resin used in the fluorescent color-converting films in the present invention is a light-curable or joint-light/heat-curable resin that is made insoluble and unmeltable by carrying out light and/or heat treatment, thus generating radical species or ionic species and hence polymerizing or crosslinking the resin.

10 3) Color filter layers

In the case that sufficient color purity cannot be obtained with only the color-converting layers, the color-converting filters are made to be laminates of color filter layers and the color-converting layers.

The color filter layers preferably have a thickness of 1 to 1.5 μm .

15 Next, examples of the present invention will be described together with a comparative example, with reference to the drawings.

(Example 1)

FIG. 1 is a schematic sectional view of an organic EL display used in an example of the present invention. FIG. 2 is a schematic view of a stress-relieving layer of the present invention in the case of being provided on an upper surface of a color-converting substrate.

[TFT substrate 1, TFTs 2, anodes 3]

As shown in FIG. 1, a constitution was adopted in which bottom gate type TFTs 2 were formed on a glass substrate 1, and the source of each TFT 2 was

25

connected to an anode 3.

For each of the anodes 3, Al, which was connected to the source of the corresponding TFT via a contact hole formed in an insulating film on the TFT, not shown, was formed as a lower part, and IZO (InZnO) was formed on the upper
 5 surface thereof.

The Al is provided to reflect light emitted from a light-emitting layer so that light is discharged efficiently from the top, and to reduce the electrical resistance.

The thickness of the Al film was made to be 300nm. The upper part IZO has a high work function, and hence is provided so that holes can be injected efficiently. The
 10 thickness of the IZO was made to be 200nm.

{

Organic EL layer 4}

An organic EL layer 4 was constituted from the four layers of anodes 3 / hole injection layer / hole transport layer / organic EL light-emitting layer / electron
 15 injection layer / cathode 5 excluding the electrodes.

The substrate 1 having the anodes 3 formed thereon was put into a resistive heating vapor deposition apparatus, and the hole injection layer, the hole transport layer, the organic EL light-emitting layer, and the electron injection layer were deposited in this order without releasing the vacuum. During the deposition, the
 20 pressure inside the vacuum chamber was reduced down to 1×10^{-4} Pa. Copper phthalocyanine (CuPc) was formed to a thickness of 100 nm as the hole injection layer. 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (α -NPD) was formed to a thickness of 20 nm as the hole transport layer. 4,4'-bis(2,2'-diphenylvinyl)biphenyl (DPVBi) was formed to a thickness of 30 nm as the organic EL light-emitting layer.

25 An aluminum chelate (Alq) was formed to a thickness of 20 nm as the electron

injection layer.

After that, a transparent cathode 5 was formed using a metal mask without releasing the vacuum.

The transparent cathode 5 was formed by depositing metallic Mg/Ag, which
 5 has a low work function as required for injection of electrons, to a thickness of 2 nm using a codeposition method, and then depositing an IZO film thereon to a thickness of 200 nm using a sputtering method.

{

Passivation layer 6}

10 An SiON_x film was deposited by sputtering to a thickness of 300 nm as a passivation layer 6.

{

Color filter layers 10}

A blue filter material (made by Fuji Hunt Electronics Technology; Color
 15 Mosaic CB-7001) was applied using a spin coating method onto a glass substrate 13, and then patterning was carried out using a photolithography method, thus obtaining a line pattern with a thickness of 6 μm.

After that, a photoresist (JNPC-48 made by JSR) was similarly applied using a spin coating onto the glass substrate 13, and then patterning was carried out using a
 20 photolithography method, thus forming a line pattern with a thickness of 5.5 μm (not shown) on the blue filter pattern, whereby color filter layers 10 of thickness 11.5 μm comprising a laminate of the blue filter pattern and a transparent resist pattern were obtained.

{

25 Color-converting layers 11 and 12}

Red and green color filter layers (not shown) made of similar color filter materials to the blue filter material were applied using a spin coating method onto the substrate 13, and then patterning was carried out using a photolithography method, thus obtaining line patterns of green color filters and red color filters with a thickness
5 of 1.5 μm .

Next, Coumarin 6 (0.7 parts by weight) as a green fluorescent colorant was dissolved in 120 parts by weight of a propylene glycol monoethyl acetate (PGMEA) solvent. 100 parts by weight of a photopolymerizable resin 'V259PA/P5' (trade name, Nippon Steel Chemical Co., Ltd.) was then added and dissolved, thus obtaining
10 a coating liquid. This coating liquid was applied using a spin coating method onto the green color filters on the substrate 13, and then patterning was carried out using a photolithography method, thus obtaining a line pattern with a thickness of 10 μm , whereby green color-converting layers 11 of thickness 11.5 μm comprising a laminate of the green filter pattern and the green color-converting pattern were obtained.

Furthermore, Coumarin 6 (0.6 parts by weight), Rhodamine 6G (0.3 parts by weight) and Basic Violet 11 (0.3 parts by weight) as red fluorescent colorants were dissolved in 120 parts by weight of a propylene glycol monoethyl acetate (PGMEA) solvent. ~~100~~One hundred parts by weight of a photopolymerizable resin
15 'V259PA/P5' (trade name, Nippon Steel Chemical Co., Ltd.) was then added and dissolved, thus obtaining a coating liquid. This coating liquid was applied using a
20 spin coating method onto the red color filters on the substrate 13, and then patterning was carried out using a photolithography method, thus obtaining a line pattern with a thickness of 10 μm , whereby red color-converting layers 12 of thickness 11.5 μm comprising a laminate of the red filter pattern and the red color-converting pattern
25 were obtained.

A black mask 9 (thickness 11.5 μm) was formed between the color-converting layers of the various colors. As a black mask having high thermal conductivity, first 500 nm of chromium oxide was formed by sputtering using a mask enabling formation of a lattice pattern on walls of the color-converting layers. Next, using a similar mask, an SiN film was formed by sputtering around the red, green and blue sub-pixels so as to be the same thickness. The pitch of the pixels was 0.3×0.3 mm, and the shape of the sub-pixels of the various colors was 0.1×0.3 mm.

{

Stress-relieving layer 8}

ZPN 1100 (made by Nippon Zeon Co., Ltd.) was applied using a spin coating method onto an upper surface of the color-converting layers, and then patterning was carried out using a photolithography method, thus forming a stress-relieving layer having a reverse tapered shape provided at edges of the color-converting layers. The thickness of the stress-relieving layer was 5 μm from the surface of the color-converting layers. Next, leaving only walls of the stress-relieving layer, an upper surface of the stress-relieving layer and upper surfaces of the color-converting layers were coated with an OFPR 8000 photoresist (made by Tokyo Ohka Kogyo Co., Ltd.). A Benefix VL visible light-curable resin (made by Ardel, refractive index 1.48) was further coated thereon, and then irradiation with visible light was carried out; the OFPR 8000 was then removed using a stripping liquid 104 (made by Tokyo Ohka Kogyo Co., Ltd.), whereby a stress-relieving layer 8 in which only the walls of the ZPN 1100 were coated with Benefix VL was formed.

{Bonding together}

The organic light-emitting device and the color-converting substrate obtained as described above were bonded together using an adhesive. As the adhesive

forming the adhesive layer 7, a polycarbonate curable by joint use of visible light and heat (made by Ardel, refractive index 1.56) was used.

(Example 2)

5 Manufacture was carried out as in Example 1, except that for the stress-relieving layer 8, ZPN 1100 having fine carbon particles (thermal conductivity $90 \text{ W m}^{-1} \text{ K}^{-1}$) dispersed therein was used, and modification of the walls with Benefix VL was not carried out. The mixing ratio of the resin and the carbon was 5:1 in terms of weight.

10

(Comparative example)

FIG. 3 is a schematic sectional view showing the constitution of a comparative example; members having the same function as members shown in FIG. 1 are given the same reference numerals as in FIG. 1, and detailed description thereof will be omitted here. In the comparative example of FIG. 3, a gap-adjusting frame structure 14 was formed around the periphery of a display part of the color-converting layers using a JNPC-48 negative type resist (made by JSR). Next, without a stress-relieving layer as shown in FIG. 1, the color-converting substrate side and the organic light-emitting device substrate side were bonded together with a polycarbonate forming an adhesive layer 7.

15

20

(Evaluation)

Evaluation was carried out for the following items. The results are shown in Table 1.

25 1. Heat cycle test:

Each manufactured display was subjected to a heat cycle test ($-40^{\circ}\text{C} \leftrightarrow 95^{\circ}\text{C}$, 120 cycles, temperature raising/decreasing time less than 5 min), and it was observed whether or not abnormalities in the form arose.

2. Contrast

- 5 For the displays, a comparison was carried out of the contrast for the case of irradiating light from a fluorescent lamp (1000 lx) onto the display surface from an angle of 45°C .

3. Driving lifetime

- Each display was subjected to continuous driving using low-current passive
10 driving with a constant current value, and a comparison was carried out of the driving time until the retention rate of the brightness relative to the initial brightness reached 50% due to the driving.

4. Efficiency

- A comparison was carried out through the brightness in the case of driving
15 each of the displays with a constant current value.

In Table 1, a result greater than 1.0 indicates a better result than for the comparative example; from the results of Table 1, it was found that the examples are superior to the comparative example.

- 20 (Table 1)

Summary of evaluation results

	Example 1	Example	Comparative example
1. Heat cycle	No change in form	No change in form	Peeling away of light-emitting device occurs
2. Contrast*	1.0	3.0	1.0
3. Driving lifetime*	1.0	1.5	1.0
4. Efficiency*	1.3	1.0	1.0

* For the contrast, the driving lifetime, and the efficiency, the value for the comparative example was taken as 1.0.

INDUSTRIAL APPLICABILITY

5

According to the present-invention, an organic EL display having high reliability and high efficiency can be provided.

Specifically, the organic EL display of the present-invention is made to have a constitution in which a stress-relieving layer made of a material having a higher elasticity than an adhesive layer is provided at edges of color-converting filters that
10 are constituted from color filter layers alone, or color filter layers and color-converting layers, and are formed on a transparent supporting substrate; as a result, it can be made to be such that stress arising when bonding the color-converting filters and the organic light-emitting device together, or when there are changes in the
15 environment in which the display is placed is absorbed by the stress-relieving layer, and hence the light-emitting device is not damaged.

Moreover, by making the refractive index of the stress-relieving layer be lower than that of the adhesive layer, reflection at walls of the stress-relieving layer is promoted, and hence the component of the light emitted by the light-emitting device
20 that escapes sideways can be reduced.

Furthermore, by making the structure of the stress-relieving layer be a reverse tapered shape relative to the color-converting filters as shown in FIG. 1, the efficiency of extracting light is further improved.

Moreover, the component reflected at the walls of the stress-relieving layer
25 may cause a drop in contrast. In the case that the contrast is considered to be more

important than the efficiency of extracting light, the material of the stress-relieving layer is made to be a material that absorbs light, whereby the contrast of the panel is improved.